



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C09K 11/66</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 99/32575</b> <b>(43) International Publication Date:</b> 1 July 1999 (01.07.99)
<b>(21) International Application Number:</b> PCT/IB98/01934 <b>(22) International Filing Date:</b> 3 December 1998 (03.12.98) <b>(30) Priority Data:</b> 97204031.5           19 December 1997 (19.12.97)   EP 98202063.8           22 June 1998 (22.06.98)       EP <b>(71) Applicant:</b> KONINKLIJKE PHILIPS ELECTRONICS N.V. [NL/NL]; Groenewoudseweg 1, NL-5621 BA Eindhoven (NL). <b>(71) Applicant (for DE only):</b> PHILIPS PATENTVERWALTUNG GMBH [DE/DE]; Röntgenstrasse 24, D-22335 Hamburg (DE). <b>(71) Applicant (for SE only):</b> PHILIPS AB [SE/SE]; Kottbygatan 7, Kista, S-164 85 Stockholm (SE). <b>(72) Inventors:</b> JUSTEL, Thomas; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL). NIKOL, Hans; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL). RONDA, Cornelis, Reinder; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL). DE HAIR, Johannes, Theodorus, Wilhelmus; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL).		<b>(74) Agent:</b> BOSMA, Rudolphus, H., A.; Internationaal Octrooi- reau B.V., P.O. Box 220, NL-5600 AE Eindhoven (NL).  <b>(81) Designated States:</b> CN, JP, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> LUMINESCENT MATERIAL  <b>(57) Abstract</b>  <p>The invention relates to a luminescent material of the general formula <math>(Ba_xSr_{1-x-y}Pb_y)_2Mg(BO_3)_2</math>, wherein <math>0 \leq x \leq 0.999</math> et <math>0.0005 \leq y \leq 0.05</math>. Luminescent materials of this general formula are very suitable for use in low pressure mercury discharge lamps for tanning purposes. The invention also relates to a method for preparing this luminescent material.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

## Luminescent Material.

The invention relates to a luminescent material, a luminescent screen and a low pressure mercury lamp comprising such a luminescent screen. The invention also relates to a method for preparing the luminescent material.

5


In US 4,703,224 a low pressure mercury discharge lamp for tanning purposes is disclosed comprising a luminescent screen containing, in addition to a UV-B phosphor,  $\text{Sr}_2\text{P}_2\text{O}_7:\text{Eu}^{2+}$  and  $\text{Ba}_2\text{P}_2\text{O}_7:\text{Eu}^{2+}$  as UV-A phosphors. This composition of the luminescent screen allowed the low pressure mercury discharge lamp (further also called lamp) to simulate the spectrum of the sun in the UV-region. A disadvantage of the used luminescent materials, however, is the fact that they both absorb radiation with a wavelength between 280 nm and 350 nm relatively strongly. As a result the short-wavelength radiation generated by the luminescent screen is to a relatively large extent reabsorbed and converted into long-wavelength radiation. The amount of short-wavelength radiation reabsorbed by the luminescent screen is a very strong function of its thickness. For this reason thickness-  
variations in the luminescent screen along the lamp vessel of the lamp cause relatively large differences between the spectra of the light emitted from different places on the surface of the lamp vessel.

20

The invention aims to provide a luminescent material mainly emitting in the UV-A region of the spectrum that has a low absorption of short-wave radiation and is therefore very suitable for use in the luminescent screen of a low pressure mercury discharge lamp for tanning purposes.

25

A luminescent material according to the invention is of general formula



wherein  $0 \leq x \leq 0.999$ ,  $0.0005 \leq y \leq 0.05$ .

It has been found that a luminescent material according to the invention  
5 has its main emission between 370 nm and 390 nm and absorbs only a relatively small  
amount of radiation between 280 nm and 350 nm. In case the Sr content of the luminescent  
material according to the invention is increased, the maximum of the emission band is shifted  
to a shorter wavelength which results in a smaller amount of absorption of radiation between  
280 nm and 350 nm. Table 1 shows the emission maximum EM, the full width at half  
10 maximum FWHM and the absorption coefficient  $AQ_{254}$  of a luminescent material according  
to the invention for different values of x when  $y = 0.005$ . Table 2 shows the emission  
maximum EM, the full width at half maximum FWHM, the absorption coefficient  $AQ_{254}$  and  
the quantum efficiency QE for different values of y of a luminescent material according to  
the invention for different values of y when the luminescent material contains no Sr.

15 It has also been found that a close simulation of the UV-spectrum of  
sunlight can be obtained for low pressure mercury discharge lamps with a luminescent screen  
that comprises, apart from a luminescent material according to the invention, for instance  
lanthanum phosphate activated with cerium and barium silicate activated with lead.

A luminescent material according to the invention can be prepared by  
20 means of a method comprising the following steps:  
- mixing of  $BaCO_3$ ,  $SrCO_3$ ,  $MgO$ ,  $H_3BO_3$  and  $PbO$ ,  
- heating the obtained mixture in an oxygen containing atmosphere, and  
- grinding the resulting material. Preferably the last two steps of the method are  
repeated. It has been found that good results are obtained in case the heating is done at 900  
25 C.

In a typical example a luminescent material not containing Sr was  
prepared by mixing  $BaCO_3$ ,  $MgO$ ,  $H_3BO_3$  and  $PbO$  in an agate mortar. The mixture was  
subsequently heated in an oxygen containing atmosphere, and ground. The last two steps of  
this preparation method were repeated and the resulting luminescent material was stored in a  
30 dry container.

TABLE 1


	x	EM(nm)	FWHM(nm)	AQ <sub>254</sub> (%)
5	1.0	380	53	83
	0.75	375	59	94
	0.5	362	62	93
	0.25	346	77	88
10	0.0	340	57	85

TABLE 2

	y	EM(nm)	FWHM(nm)	QE(%)	AQ <sub>254</sub> (%)
15	0.005	380	53	63	80
	0.01	380	53	60	83
	0.02	380	53	50	90
20					

CLAIMS:

1. Luminescent material of general formula



5 wherein  $0 \leq x \leq 0.999$ ,  $0.0005 \leq y \leq 0.05$ .

2. Luminescent screen comprising a bearer provided with a luminescent material, characterized in that the luminescent screen comprises a luminescent material as claimed in claim 1.

10

3. Low pressure mercury discharge lamp provided with a luminescent screen as claimed in claim 2.

4. Method for preparing a luminescent material as claimed in claims 1-5,  
15 comprising the following steps:

- mixing of  $\text{BaCO}_3$ ,  $\text{SrCO}_3$ ,  $\text{MgO}$ ,  $\text{H}_3\text{BO}_3$  and  $\text{PbO}$ ,
- heating the obtained mixture in an oxygen containing atmosphere, and
- grinding the resulting material.

- 20 5. Method according to claim 4, wherein the last two steps of the method are repeated.

6. Method according to claim 4 or 5, wherein the heating is done at 900 C.

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/IB 98/01934

## A. CLASSIFICATION OF SUBJECT MATTER

IPC6: C09K 11/66

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: C09K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPODOC, WPI

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4703224 A (KENDRICK D. RATTRAY ET AL), 27 October 1987 (27.10.87)  -- -----	1-6



Further documents are listed in the continuation of Box C.



See patent family annex.

\* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

4 March 1999

Date of mailing of the international search report

10 -03- 1999

Name and mailing address of the ISA/  
Swedish Patent Office  
Box 5055, S-102 42 STOCKHOLM  
Facsimile No. +46 8 666 02 86

Authorized officer

Britt-Marie Lundell

Telephone No. +46 8 782 25 00

Information on patent family members

02/02/99

International application No.

**PCT/IB 98/01934**

Publication  
date

27/06/89